

Model No.: GP24PL

Document Number: TG R03 L001

Revision: 01

Page 1 of 10

Specification for GP24PL

1.5V R03 AAA size

Zinc Manganese dioxide Battery

| Approved by Customer | |
|---|--|
| Issued Date: | |
| | |
| Approved by GP Batteries International Ltd. | |
| Issued Date: | |



Product Specifications

Model No.: GP24PL

Document Number: TG R03 L001 Revision: 01 Page 2 of 10

Revision History

| Revision No. | Revision Content | Issue Date |
|--------------|-------------------|------------|
| 01 | New specification | 2014-08-15 |



Model No.: GP24PL

Document Number: TG R03 L001 Revision: 01 Page 3 of 10

1. Applicability

This specification is applicable to GP24PL (No Mercury & Cadmium added).

2. General

2.1 Type designation : R03(IEC/JIS),24D(ANSI)

2.2 Nominal voltage : 1.5V

2.3 Chemical system : (-) Zn ZnCl2,NH4Cl MnO2 (+)

2.4 Shape and dimension : Refer to Drawing 1.

2.5 Weight (reference) : 8.4g2.6 Effective period : 36 months2.7 Date code : MM-YYYY

(e.g. 01-2017 represents expiry date of January, 2017)

2.8 Jacket :Foil label (Refer to Drawing 2)

3. Appearance

There shall be no dirt, scratch or deformation detrimental to practical service in appearance.

4. Electrical Characteristics

4.1 Test method

Method of sampling : ISO2859-1 Level single sampling normal inspection.

Voltmeter : Digital Voltmeter (DVM) with the precision of 1mV (internal resistance

not less than 1 Megohm)

Test temperature : 20±2°C

4.2 Open-circuit Voltage (OCV)

| Initial | 12 months | 24 months |
|------------|------------|------------|
| 1.60~1.73V | 1.54~1.73V | 1.52~1.73V |

4.3 Closed-circuit Voltage (CCV)

| Initial | 12 months | 24 months | |
|-------------|-------------|-------------|--|
| Above 1.50V | Above 1.44V | Above 1.40V | |

Load resistance : 15 ohm $\pm\,0.5\%$ (measure time : 0.8 seconds)

^{*}The initial OCV & CCV test shall commence within 60 days of manufacture, during 61 days ~12 months storage the OCV &CCV accept/reject according to 12 months, during 13 ~24 months storage the OCV &CCV accept/reject according to 24 months. During this period, the cells shall be stored under room temperature conditions.(20±2°C and 55±20% relative humidity)



Model No.:GP24PL

Document Number: TG R03 L001 Revision: 01 Page 4 of 10

5. Operating Temperature: 0°C to 45°C (60±20%RH)

6. Storage Temperature: -10°C to 25°C (60±20%RH)

7. Service Output

7.1 Test method

- (1) The resistance of external discharge circuit shall be as specified plus or minus 0.5%.
- (2) The duration of discharge time periods shall be as specified plus or minus 1%.
- (3) Storage shall be at 20±2°C, 55±20%RH and discharge tests shall be at 20±2°C, 55±20%RH.

7.2 Service Life

| Discharge | | EV | Standard | Initial | | 12Months | 24Months Application | Application | |
|--|-------------|------|-----------------------|---------|-------|----------|----------------------|-------------------|--|
| | Items | | Otaridard | Typical | MAD | MAD | MAD | Application | |
| 15ΩC | ontinuous | 0.9V | - | 240M | 200M | 190M | 170M | Reference test | |
| 5.1Ω | 4M/H-8H/D | 0.9V | IEC60086 GB/T 8897 | 90M | 70M | 60M | 58M | Portable lighting | |
| 10Ω | 1H/D | 0.9V | IEC60086 GB/T 8897 | 2.7H | 2.3H | 2.1H | 1.9H | Digital audio | |
| 75Ω | 4H/D | 0.9V | IEC60086 GB/T 8897 | 30.0H | 25.5H | 23.5H | 22.0H | Radio/Clock | |
| 24Ω | 15S/M, 8H/D | 1.0V | IEC60086 GB/T 8897 | 9.0H | 7.5H | 6.5H | 6.2H | Remote control | |
| S: Second M: Minute H: Hour D: Day EV: End-point Voltage MAD: Minimum Average Duration | | | | | | | | | |

^{*}The initial discharge test shall commence within 60 days of manufacture. The initial service life accept/reject according to initial MAD, during 61 days ~12 months storage the service life accept/reject according to 12 months MAD, during 13 ~24 months storage the service life accept/reject according to 24 months MAD.

8. Electrolyte Leakage

| | Test Items | Test Conditions | Requirements | |
|-----|-----------------------|---|---|--|
| 8.1 | Arrival at warehouse. | within two months after shipping | There shall be no leakage observed | |
| 8.2 | Long term storage | Within 24 months of storing at -10°C to 25°C (60±20%RH) | with the naked eye, and no | |
| 8.3 | High Temperature | Test specimens shall be kept standing at 45±2 and less than 70% RH for 30 days. | bulging or deformation of batteries in excess of dimensions shown in the Drawing 1 | |
| 8.4 | Over-discharge | 15Ω Continuous discharge until to EV=0.6V (Test conditions:20 \pm 2°C and 55 \pm 20%RH) | | |

During this period, the cells shall be stored under room temperature conditions.(20±2°C and 55±20% relative humidity)



Model No.: GP24PL

Document Number: TG R03 L001 Revision: 01 Page 5 of 10

9. Quality Assurance

| | DESCRIPTION | SAMPLING PLAN | |
|------------------------------|------------------------------------|-------------------|--|
| Battery dimensions | 3 | AQL=0.25 (Note 4) | |
| Appearance | Major defects (Rust etc.) | AQL=0.25 (Note 4) | |
| | Minor defects (Scratch Stain etc.) | AQL=1.0 (Note 4) | |
| Open-circuit Voltag | le (OCV) | AQL=0.65 (Note 4) | |
| Closed-circuit Voltage (CCV) | | AQL=1.0 (Note 4) | |
| Service output | | Note 1 | |
| Leakage 8.1 | eakage 8.1 AQL=0.25(Note 4) | | |
| 8.2 | | AQL=0.25(Note 4) | |
| 8.3 | | Note 2 | |
| 8.4 | | Note 3 | |

- Note 1: Acceptance / rejection in accordance with IEC60086-1 Sub-clause 5.3.
 - 1) Test nine batteries.
 - 2) Calculate the average without the exclusion of any result.
 - 3) If this average is equal to or greater than the specified figure and no more than one battery has a service output of less than 80% of the specified figure, the batteries are considered to conform for service output.
 - 4) If this average is less than the specified figure and/or more than one battery has a service output of less than 80% of the specified figure, repeat the test on another sample of nine batteries and calculate the average as previously.
 - 5) If the average of this second test is equal to or greater than the specified figure and no more than one battery has a service output of less than 80% of the specified figure, the batteries are considered to conform for service output.
 - 6) If the average of second test is less than the specified figure and/or more than one battery has a service output of less than 80% of the specified figure, the batteries are considered not to conform and no further testing is permitted.

Note 2: Sample size: n=20

Judgement: Ac=1 Re=2


Note 3: Sample size: n=9

Judgement: Ac=0, Re=1

Note 4: AQL General Inspection level II, single sampling plan.

10. Remark

Regarding the untouched items in this specification, please refer to IEC60086-1 & IEC60086 -2 & IEC60086-5





Model No.: GP24PL

Document Number: TG R03 L001 Revision: 01 Page 6 of 10

11. Packaging

11.1 Normal Packaging(See attached packing diagram)

1Pack(2pcs) 1Display Box(20Packs,40pcs) 1Inner-box(5Display Boxes,200pcs)

1Outer-box(5 Inner-Boxes,1000pcs)

11.2 Special Packaging

Packaging form shall be agreed by both parties.

12. Precaution & Handling

- 1) Do not disassemble or short-circuit batteries.
- 2) Do not recharge batteries.
- 3) Do not dispose of batteries in fire.
- 4) Do not allow metal objects to contact the battery terminals.
- 5) Do not mix with used or other battery type (such as alkaline with carbon zinc).
- 6) Do not solder the batteries directly. If soldering or welding connection to the battery is required, consult our engineer for proper methods.
- 7) Do not over-discharge batteries. Force discharging batteries by external power source in a series may cause explosion.
- 8) To install or remove batteries, follow the equipment manufacturer's instructions.
- 9) Keep battery away from small children. If swallowed, consult a physician at once.
- 10) Remove batteries from device when it is not in use.

13. Storage

- 1) Store in a cool, dry place before use.
- 2) Do not leave the batteries in an atmosphere over the temperature of 30°C or over the relative humidity of 85% for a long time.

Product Specifications

Model No.: GP24PL

Document Number: TG R03 L001 Revision: 01 Page 7 of 10


14. Reference Specifications (the latest edition of the referenced document applies)


- 14.1 IEC60086-1/GB/T 8897.1 Primary batteries part 1: General.
- 14.2 IEC60086-2/GB/T 8897.2 Primary batteries part 2: Physical and electrical specifications
- 14.3 IEC60086-5/GB 8897.5 Primary batteries part 5: Safety of batteries with aqueous electrolyte
- 14.4 ISO2859-1 Sampling procedures for inspection by attributes -- Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection
- 14.5 2006/66/EC: Eu Battery Directive

Product Specifications

Model No.: GP24PL

Document Number: TG R03 L001 Revision: 01 Page 8 of 10





Product Specifications

Model No.: GP24PL

Document Number: TG R03 L001 Revision: 01 Page 9 of 10

Drawing 2



Product Specifications

Model No.: GP24PL

Document Number: TG R03 L001 Revision: 01 Page 10 of 10

Packing diagram

